



NATIONAL MAGNETICS GROUP, INC.

MANUFACTURERS OF MAGNETIC AND ADVANCED MATERIALS

AFFILIATE: TCI CERAMICS, INC.

H2 Material


A NiZn ferrite designed for EMI suppression from 20 MHz to 250 MHz, as well as for inductive applications including high frequency common-mode chokes.

Specifications


Property	Unit	Symbol	Standard Test Conditions	Value
Initial Permeability		μ_i	Frequency=10 kHz; B<10 gauss	850 \pm 20%
Saturation Flux Density	gauss	B_s	H=10 oersted	\approx 3200
Residual Flux Density	gauss	B_r		\approx 1300
Coercive Force	oersted	H_c		\approx 0.45
Loss Factor	10^{-6}	$\text{Tan}\delta/\mu_i$	Frequency=1 MHz; B=1 gauss	\leq 250
Temperature Coefficient of Initial Permeability (20-70°C)	%/°C			\leq 1.25
Volume Resistivity	Ω cm	ρ		$\approx 10^7$
Curie Temperature	°C	T_c		\geq 155

Note: values are typical and based on measurements of a standard toroid at 25 °C


Complex Permeability vs. Frequency




B – H Loop



Initial Permeability vs. Temperature



Change of Impedance vs. Temperature



FERRITES • MAGNETS • IRON CORES • GARNETS • DIELECTRICS • RESONATORS • POWDERS

1210 WIN DR.
BETHLEHEM, PA 18017-7061

REV1

TEL: 610-867-7600 • FAX: 610-867-0200 • EMAIL: sales@magneticsgroup.com