



# NATIONAL MAGNETICS GROUP, INC.

MANUFACTURERS OF MAGNETIC AND ADVANCED MATERIALS

AFFILIATE: TCI CERAMICS, INC.

## M29

### Material


A MnZn ferrite specifically designed for power applications operating in frequencies up to 2 MHz.

### Specifications


Property	Unit	Symbol	Standard Test Conditions	Value
Initial Permeability		$\mu_i$	Frequency=10 kHz; B<10 gauss	2900 $\pm$ 20%
Saturation Flux Density	gauss	$B_s$	H=10 oersted	$\approx$ 4700
Residual Flux Density	gauss	$B_r$		$\approx$ 1000
Coercive Force	oersted	$H_c$		$\approx$ 0.18
Loss Factor	$10^{-5}$	$\text{Tan}\delta/\mu_i$	Frequency=0.1 MHz; B=1 gauss	$\leq$ 5
Temperature Coefficient of Initial Permeability (20-70°C)	%/°C			$\leq$ 0.7
Volume Resistivity	$\Omega$ cm	$\rho$		$\approx 10^3$
Curie Temperature	°C	$T_c$		$\geq$ 185

Note: values are typical and based on measurements of a standard toroid at 25 °C


Complex Permeability vs. Frequency




B - H Loop



Initial Permeability vs. Temperature



Power Loss Density vs. Flux Density



FERRITES • MAGNETS • IRON CORES • GARNETS • DIELECTRICS • RESONATORS • POWDERS

1210 WIN DR.

BETHLEHEM, PA 18017-7061

TEL: 610-867-7600 • FAX: 610-867-0200 • EMAIL: [sales@magneticsgroup.com](mailto:sales@magneticsgroup.com)