



NATIONAL MAGNETICS GROUP, INC.

MANUFACTURERS OF MAGNETIC AND ADVANCED MATERIALS

AFFILIATE: TCI CERAMICS, INC.

P

Material


An MnZn ferrite designed for open circuit applications such as inductors and antennas for frequencies up to 3 MHz.

Specifications


Property	Unit	Symbol	Standard Test Conditions	Value
Initial Permeability		μ_i	Frequency=10 kHz; B<10 gauss	$\approx 600 \pm 20\%$
Saturation Flux Density	gauss	B_s	H=5 oersted	≈ 2800
Residual Flux Density	gauss	B_r		≈ 1200
Coercive Force	oersted	H_c		≈ 0.6
Loss Factor	10^{-6}	$\tan\delta/\mu_i$	Frequency=0.2 MHz; B=1 gauss	≤ 25
Temperature Coefficient of Initial Permeability (20-70°C)	%/°C			≤ 0.1
Volume Resistivity	Ω cm	ρ		$\approx 10^2$
Curie Temperature	°C	T_c		≥ 150

Note: values are typical and based on measurements of a standard toroid at 25 °C


Complex Permeability vs. Frequency



B – H Loop



Initial Permeability vs. Temperature



FERRITES • MAGNETS • IRON CORES • GARNETS • DIELECTRICS • RESONATORS • POWDERS

1210 WIN DR.
BETHLEHEM, PA 18017-7061